


## DOLAFLUX B 11

### Dispersing agent/deflocculant



#### Chemical basis:

Huminate-/Silicate preparation

#### Characteristics:

Appearance: grey powder  
Solubility: water-soluble  
Bulk density: approx. 800 g/l  
pH (1 %): approx. 12  
Residue on ignition: approx. 44 %

#### Shelf-life / Packaging:

12 months when stored properly and dry  
bags of 25 kg

#### Application:

DOLAFLUX B 11 can be used for the deflocculation of various raw materials and bodies of differing composition.

After deflocculation with this dispersing agent the bodies usually exhibit a high solids content. The generally broad deflocculation interval is able to compensate for raw material variations.

The deflocculating effect of DOLAFLUX B 11 is achieved by cation exchange of the additive with the ceramic body, and the associated influence on the electrical double layer of the clay mineral particles. The product is also surface-active by virtue of the components it contains. This combination of effects leads to a good breakdown of the raw materials in a relatively short time. It is associated with an increase in the green and dry breaking strength in many cases.

The amount of DOLAFLUX B 11 to be added ranges between 0.1 and 0.5 % of the solids content of the slip.

Since, on account of their differing mineralogical composition, raw materials react very differently to various deflocculants and addition quantities, we recommend to carry out comparative trials.

The above results have been obtained from trials in our laboratory and plant. In the light of changing conditions they can serve only as a guide and are therefore offered without obligation. We ask you to observe the possible rights of third parties.

Issued: 18. April 2012

Page: 1 / 1

